



EMI SHIELDING PRODUCTS FROM THE PREMIER UK MANUFACTURER

Fire Retardant Nickel Graphite Silicone EC-Q-FR

P & P Technology material reference EC-Q-FR is a fire retardant Silicone elastomer with a nickel / graphite conductive filler.

The material can be supplied in sheet, extruded or moulded form.

Our EC-Q-FR offers a high level of flame retardance (UL94 -V0), excellent performance over a wide temperature range (-50°C to +160°C) and Nickel/Graphite provides a high level of EMI screening protection.

Conductive silicone is best used where mating surfaces are smooth and well machined. They should be mounted to provide adequate volume for the material to deflect under pressure and should be compressed by between 8 and 20% of their relaxed height for solid sections and between 20 and 100% of the height of the hollow center of tubular sections. Moulded 'O' rings, gasket profiles and sheet materials all have their own compression characteristics according to how they are mounted and do not comply with the guidelines above.

The material is specially compounded to offer excellent physical and electrical properties over an effective temperature range of -55C to +160°C.

Physical Properties	Test methods	Typical values
Hardness	ASTM D-2240	60 (±5) Shore A
Specific Gravity	ASTM D-792	2.10 (±.02) g/cc
Tensile Strength	ASTM D-412	1.03 MPa
Elongation	ASTM D-412	100%
Compression Set 72 hrs @ 100°C	ASTM D-395	40% max
Electrical properties		
Volume Resistivity	Mil-G-83528C	0.1 Ω/cm max

Shielding effectiveness (Mil-G-83528) dB (Mil Std. 285 procedure)

Frequency	Attenuation
10MHz	82
400MHz	90
1GHz	90
2GHz	90
10GHz	90
18GHz	95



P & P Technology

P & P Technology, Unit 9, Hoblongs Industrial Estate, Chelmsford Road, Dunmow, Essex, CM6 1JA, UK
T: 44 (0) 1376 550525 F: +44 (0) 1376 552389 www.p-p-t.co.uk