

Neoprene Sponge (Chloroprene)

Neoprene has good resistance to heat, moderate chemicals & oils, sea water, acids, fats, greases, many solvents & ozone. It also has good flame retardant properties.

General Specification

Density average	120±30 kg/m ³
Hardness	40 IRHD base number
Compression Set	10% (23°C at 50% compression for 24 hours) maximum
Temperature Range	-34°C to 80°C continuous or 100°C intermittent
Fire Resistance	Self-extinguishing MVSS-302
Elongation at break	150%
Water Absorption by weight	5%
Compression Deflection at 25%	35-63 kPa
Tensile Strength	450 kN/m ²
Colour	Black



P & P Technology Ltd
1-3 Finch Drive, Springwood Industrial Estate
Braintree, Essex, CM7 2SF, UK
Tel: +44 (0) 1376 550525 Fax: +44 (0) 01376 552389
Email: info@p-p-t.co.uk Web: www.p-p-t.co.uk

